#### DECLARATION OF PERFORMANCES

NºIB044|CPR2006-09-25| English version - Rev 01

1. Unique identification code of the product-type:

#### 1.0577

2. Type, batch or serial number or any other element allowing identification of the construction product as required pursuant to Article 11(4):

## Plates S355J2 according to EN 10025-2

3. Intended use or use of the construction product in accordance with the applicable harmonised technical specification, as foreseen by the manufacturer:

# To be used cut to length plates in metal structures or in composite metal and concrete structures

4. Name, registered trade name or registered trade mark and contact address of the manufacturer as requires pursuant to Article 11 (5)

Industeel Belgium S.A 266,Rue de Chatelet 6030 Marchienne-au-pont Belgium Tel:+32 71 44 18 28

Email: carine.desondre@arcelormittal.com

5. Where applicable, name and contact address of the authorised representative whose mandate covers the tasks specified in Article 12(2):

## Not applicable

6. System or systems of assessment and verification of constancy of performance of the construction product as set out in Annex V:

#### System 2+

7. In case of the declaration of performance concerning a construction product covered by a harmonised standard:

#### EN 10025-2:2004

Notified factory production control certification body No(.See list below) performed the initial inspection of the manufacturing plant and of factory production control and the continuous surveillance, assessment and evaluation of factory production control and issued the certificate of conformity of the factory production control

Charleroi 1148

8. In case of the declaration of performance concerning a construction product for which a European Technical Assessment has been issued:

Not applicable

# **DECLARATION OF PERFORMANCES**

N°IB044|CPR2006-09-25| English version - Rev 01

# 9. Declared performance

Essential characteristic	Performance				Harmonised technic specification	
Tolerances on dimensions and shape  Yield Strength	Thickness, length and width EN 10029			Specification		
	Flatness on cut to length plate		EN 10029			
	Nominal thickness (mm)		Values (Mpa)			
	> \ \ \ \ \		ReH			
		16	355		1	
	16	40	345		1	
	40	63	335			
	63	80	325			
	80	100	315			
	100	150	295			
	150	200	285 275		1	
	200	250			1	
	250	400	265		1	
Tensile Strength	Nominal thickness (mm) Values (M		(Mpa)	1		
	>	<b>S</b>	Rm min	Rm max	1	
		2,99	510	680		
	2,99	100	470	630		
	100	400	450	600		
	Nominal thic			ues	-	
Elongation	> Nominal tine	kness (IIIII) ≤	min (%)	Samples	-	
		1	12	Lo=80mm		
	1	1,5	13	Lo=80mm		
	1,5	2	14	Lo=80mm		
	2	2,5	15	Lo=80mm		
	2,5	2,99	16	Lo=80mm		
	2,99	40	20	5,65√So	EN 10025-2:2004	
	40	63	19	5,65√So		
	63	100	18	5,65√So	1	
	100	150	18	5,65√So		
	150	400	17	5,65√So	1	
	Nominal thickness (mm)		Values long.		1	
Impact Test	>	≤ (IIIII)	KV mini (J)	T°	1	
	5,99	8,49	14	-20°C		
	8,49	10,99	21	-20°C		
	10.99	400	27	-20°C		
	Nominal thick		Val		1	
CEV	> ≤		%		1	
		30		0,45		
	30	150	0,4			
	150	400	0.49		i	
Durability	Nominal thickness (mm)		Values		1	
	> ≤		%		1	
		_	C ≤ 0,20	200	1	
		221	Si ≤ 0,55	S ≤ 0,025		
		30	Mn ≤ 1,60	Al ≥ 0,020		
			P ≤ 0,025	Cu ≤ 0,55		
	30	400	C ≤ 0,22	224 (21 ASSAURANCE)	1	
			Si ≤ 0,55	S ≤ 0,025		
			Mn ≤ 1,60	Al ≥ 0,020		
				Cu ≤ 0,55		

10. The performance of the product identified in points 1 and 2 is in conformity with the declared performance in point 9

This declaration of performance is issued under the responsibility of the manufacturer identified in point 4

Signed for and on behalf of the manufacturer by:

Matthieu Sinnaeve Head of Method Department- Metallurgy Charleroi, 30<sup>th</sup> may 2016 Karim Bahri Head of Quality Management System Charleroi, 30<sup>th</sup> may 2016